

Compos-a-vac® 40



Physical Property Data

Property	Method	Units		Typical Value
Thickness	ASTM D 374	Mils		3.2
Tensile Break	ASTM D 882	PSI	MD TD	6,200 4,800
Elongation	ASTM D 882	%	MD TD	170 210
Elmendorf Tear	ASTM D 1922	grams/mil	MD TD	135 230
Puncture Resistance	FTMS 101C Meth. 2065	Lbf		11.4
MVTR	ASTM 1249	grams/100 in ² / Day		0.02
OTR	ASTM D3985	cc/100 in ² / Day		0.01
Seal Strength	ASTM F 88-85	Lbs/1" Strip		12

RT Engineering 7/29/05



ITW Richmond Technology

Corporate Headquarters and Plant Location

9505 Bamboo Rd. / Houston, TX USA 77041 / 1-800-825-3766 or 713-462-6111 / Fax: 713-939-4304 / info@richmond-technology.com



ISO 9001:2000 Certificate of
Approval awarded February 24,
1993 through February 28th, 2008